

Technical Datasheet

PROBIMER[®] 77 HALOGEN-FREE SEMI-MATTE

**High Performance Photoimageable Solder Mask
Alkaline Developable Two-Component-System
for Curtain Coating Application**

- **Halogen-free – exceeds JPCA Standard**
- **Green version**
- **High resolution**
- **Excellent small hole developability with high aspect ratio**
- **Wide drying window**
- **Long hold times after drying and exposure**
- **High comparative tracking index (CTI)**
- **High dielectric strength**
- **Excellent adhesion of legend inks and conformal coatings**
- **High resistance with aggressive post solder mask processes**
- **High resolution in bar code laser process**



PRODUCT INFORMATION

General Product Overview

Probimer 77 / 9021 is a photoimageable, negative working solder mask optimized for curtain coating application. The solder mask exhibits a semi-matte surface. Probimer 77 / 9021 offers high process flexibility and excellent small hole developability with high aspect ratio. It is developed in an aqueous alkaline solution.

At present the product system is available under the designation XB 9021 and 9002.

Special Features and Benefits

- Two-component-system, semi-matte surface
- Low sublimation
- High resolution
- Excellent small hole developability with high aspect ratio
- Optimized for long hold times between individual process steps
- Wide process windows offer high flexibility
- Excellent chemical, electrical and physical end properties
- Fulfills the requirements of IPC SM-840-C, classes H & T
- Corresponds to the requirements of well-known OEMs
- High comparative tracking index (CTI) and high dielectric strength
- Excellent adhesion of conformal coatings
- High resistance with aggressive post solder mask metal finishes

Product Components

Probimer 77 / 9021 is a two-component-system. It is provided in ready-to-mix packages.

	Probimer 77 / 9021	Hardener 77 / 9002
Product Components	Resin	Hardener
Mix Ratio	8.0 kg	1.13 kg

Storage and Expiration

Probimer lacquers are complex chemical compounds. To ensure that these products exhibit consistent quality in application we recommend storage under the following conditions:

- PROBIMER 77 / 9021 in original container at 2-18°C (35.6-64.4 °F)
- Hardener 77 / 9002 in original containers at 2-18°C (35.6-64.4 °F)

Under 'EXP' on the package label, the expiry date is indicated. Within this period the product should be used.

PROCESS RECOMMENDATIONS

Room Requirements on Working Environment

In order to reach best results the following room requirements should be respected:

- Room Temperature: $22 \pm 2^{\circ}\text{C}$ ($71.6 \pm 35.6^{\circ}\text{F}$)
- Relative Humidity $50 \pm 5\%$
- Cleanroom Class 100'000
- Overpressure Cleanroom + 3 mm WS
- UV blocked light

Mixing

Thoroughly mix the two components for 10-15 minutes. Mixing should be done with gentle mechanical stirring. High shear mixing must be avoided in order to prevent entrapment of large amounts of air, which can cause bubbles and poor levelling of the printed coating.

Viscosity is then adjusted with the addition of approximately 0.5 kg of the diluent 1-Methoxy-2-propyl acetate (PMA) .

Pot Life

At room temperature the ready-to-use mixture has a pot life of 3 days.

Pre-Cleaning

For a good adhesion of the lacquer we recommend chemical and/or mechanical pre-cleaning. Hold times prior to coating have to be minimized, since oxidation may impair the adhesion of the lacquer. Only completely dried boards should be coated, this has to be ensured especially for boards with small holes (microvia technology).

Coating

For Probimer 77 / 9021 a pre-heating of the boards is not required. A wide process window of 20-50 °C (68-122 °F) surface temperature facilitates a uniform coating of the boards.

Processing Parameters	from	to	standard
Lacquer temperatures in °C (in °F)	17 (62.6)	32 (89.6)	25 (77)
Conveyor speed under curtain (m/min)	60	100	90
Viscosity at 25 °C, DIN-4-cup (s)	60	120	90
Wet weight (g/600cm ²)	4.0	8.0 ¹⁾	7.0

1) Higher wet weights can be achieved if the respective processing parameters, e.g. drying time are adjusted.

PROCESS RECOMMENDATIONS

Flash-off / Drying

Probimer 77 / 9021 offers a wide drying window of 80-90°C (176-194 °F) between 30-70 minutes.

Processing parameters for CL-lines ¹⁾	from	to	standard
Flash-off temperature in °C (in °F)	105 (191)	120 (218)	115 (239)
Cycle time (s)	20		

1) The recommended parameters are valid for CL-lines. For all other processing equipment, the optimum settings have to be defined.

Processing parameters for Phase III, Phase IV ¹⁾	from	to	standard
Flash-off temperature in °C (in °F)	45 (113)	52 (125.6)	47 (116.6)
Flash-off time (min)	10	24	12 ²⁾
Temperature setting zone 1 in °C (in °F)	135 (245)	145 (261)	140 (284)
Temperature setting zone 2 in °C (in °F)	135 (245)	145 (261)	140 (284)
Temperature setting zone 3 in °C (in °F)	135 (245)	145 (261)	140 (284)
IR rods	as needed		
Conveyor speed (m/min)	2.0		

- 1) The recommended parameters are valid for: Phase III and Phase IV. For all other processing equipment, the optimum settings have to be defined
- 2) Cycle time = 20 s.

Exposure

A hold time prior to exposure is not necessary. The spectral sensitivity is in the range of 350 - 420 nm. The exposure time depends on the parameters for the developing step.

Process Parameters	from	to	standard
Energy (mJ/cm ²) – Fe doped lamp	200 ¹⁾	400 ¹⁾	300 ¹⁾
Stouffer step clear on Cu (21-step, ΔD = 0.15)	8	12	10
Hold time after exposure	not required		

Developing

The areas of unexposed Probimer 77 / 9021 lacquer should be developed in a continuous spray developing line. Developing is carried out in a 0.8-1.2 % aqueous alkaline solution.

Process Parameters	from	to	standard
Developing temperature in °C (in °F)	30 (86)	35 (95)	32 (89.6)
Dwell time under spray (sec)	50	70	60
Spray pressure in Mpa (psi)	0.2 (20)	0.4 (40)	0.3 (30)

Inspection and Stripping

In case of mishandling during exposure, such as mis-registration, boards can be stripped at 50 °C (122 °F) with 10% NaOH solution.

PROCESS RECOMMENDATIONS

Final Curing

Thermal curing is required to ensure optimal properties in the cured film. It can be done in a standard convection oven.

Process Parameters	from	to	standard
Air temperature in °C (in °F)	145 (293)	155 (311)	150 (302)
Temperature hold time (min)	50	70	60

After curing Probimer lacquers exhibit extremely high chemical resistance and, thus, cannot be easily removed without damaging the board.

UV-Curing

After thermal curing, we recommend UV curing of 1000–2000 mJ/cm² for increased chemical resistance.

Legend Inks and Conformal Coatings

In general, legend inks and conformal coatings exhibit good to excellent adhesion to boards coated with Probimer 77 / 9021. However, due to the large variety of available products preliminary trials are strongly recommended.

Production Release Trials

A variety of flow agents, soldering machines and soldering techniques as well as cleaning processes are used to mount components on circuit boards. Adjustment of the processing parameters and design guidelines to ensure optimal use of solder masks leads to the best overall results. Users should carry out their own tests prior to release for production runs.

PROPERTIES & APPROVALS

Physical Properties

Physical Properties		
Solid content ready for use	PR 2/85 (internal test norm)	60 weight %
Halogen content level	JPCA standard	< 500 ppm
Adhesion on copper (cross hatch)	ISO 2409	0-1 GT
Pencil hardness	IPC TM 650 2.4.27.2a	7-8 H
Resolution (solder dams after HAL)		2-3 mil

Chemical Properties

Chemical Properties		
Solvent resistance	Isopropanol	> 1h
	MEK	> 1h
	1,1,1-Trichlorethane	> 1h
	Methylenchloride	> 30 min.
Resistance to	E'less Ni/Au	passed
	E'less Sn, Ag	passed
	Org. Surface Passivations	passed
Ionic contamination	IPC TM 650 2.3.28	passed

Electrical Properties

Electrical Properties		
Dielectric strength	IEC 60243-1	130-150 V/μm
Surface resistance	IEC 60167	10^{14} - $10^{15} \Omega$
Volume resistivity	IEC 60093	10^{15} - $10^{16} \Omega/\text{cm}$
Comparative Tracking Index (CTI)	IEC 60112	600 – 0.0 V ¹⁾
Dielectric constant ϵ_r at 1 MHz	IEC 60250	3.8-4.2
Dielectric loss factor $\tan \delta$ at 50 Hz	IEC 60250	(77 °F) 25 °C 1.1 % ± 0.1
		(122 °F) 50 °C 2.7 % ± 0.2
		(167 °F) 75 °C 6.1 % ± 0.3
		(212 °F) 100 °C 9.7 % ± 0.4
		(248 °F) 120 °C 17.2 % ± 0.5

1) on CTI 400 laminate or with double coating

Approvals

Approvals		
UL 94 V-0	Underwriter Laboratories Inc.	Internal test passed
IPC SM-840 C, Classes H&T ¹⁾	Trace Laboratories	Internal test passed
Bellcore TR-TSY-00078	Internal test	passed

1) The norm IPC SM 840 C, H&T, includes the following tests:
 Visual inspection, fungus resistance, hydrolytic stability, dielectric strength, dimensional stability, adhesion on copper, machinability, abrasion, pencil hardness, resistance to solvents and fluxes, solderability and resistance to solder, insulation resistance before and after soldering, electro migration, thermal shock.

SAFETY AND TECHNICAL SUPPORT

Safety

When working with our products, the appropriate hygiene precautions and safety regulations should always be observed. For details, please see our Material Safety Data Sheets.

Probimer products contain flammable solvents. When the line is in operation no open flame or light is allowed in the vicinity. Before carrying out maintenance or repair work the line should be cleaned and the work area thoroughly ventilated.

Disclaimer

IMPORTANT LEGAL NOTICE: Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (Hong Kong) Ltd., or its appropriate affiliate ("Huntsman"). The following supercedes Buyer's documents.

WARRANTY: Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

DISCLAIMER AND LIMITATION OF LIABILITY: EXCEPT AS SET FORTH ABOVE, HUNTSMAN MAKES NO OTHER WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any patent. Buyer is responsible to ensure that its intended use of the Product does not infringe any intellectual property rights. Huntsman's maximum liability for any claim related to the Products or breach of an agreement associated therewith shall be limited to the purchase price of the Products or portion thereof to which such claim pertains. **IN NO EVENT SHALL HUNTSMAN BE LIABLE FOR ANY CONSEQUENTIAL, INCIDENTAL, SPECIAL OR PUNITIVE DAMAGES, INCLUDING BUT NOT LIMITED TO ANY DAMAGES FOR LOST PROFITS OR BUSINESS OPPORTUNITIES OR DAMAGE TO REPUTATION.**

WARNING: Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product described herein has not been tested for, and is therefore not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses. Furthermore, Huntsman shall not be liable for, and Buyer assumes all risks related to, the technical or other information or advice contained herein, or hereafter provided by Huntsman whether or not at Buyer's request.

Probimer[®] is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all countries.

Status: April 2006